

Chemical Resistance Guide for Finite Green FNG100

Code Letter	Chemical	CAS Number	EN 374 Performance Level
J	n-Heptane	142-82-5	3
K	Sodium hydroxide 40%	1310-73-2	6
T	Formaldehyde 37%	50-00-0	6

EN 374 Performance Levels

Permeation Performance Level	1	2	3	4	5	6
Breakthrough Time (Minutes)	> 10	> 30	> 60	> 120	> 240	> 480

The information contained here is advisory and is intended to guide and inform only. This information is based on the view of Polyco Healthline Limited in light of all available data and is not subject to any guarantee on our part regarding the performance of a particular glove style.

It is important to note that the performance of these gloves may be different if mixtures of chemicals are involved. It is impossible to test every situation encountered and all chemicals and mixtures of chemicals.

4th February 2020